

NanoPro™ A-3012

Acid Stable Membrane Data Sheet

Product description

Membrane Chemistry: Proprietary Composite Nanofiltration Membrane

Membrane Type: Acid Stable Nanofiltration Membrane

2540/4040 Spiral Wound Element

Construction*: Feed Spacer: 31 mil, 46 mil

Permeate Tube: Noryl; Polysulfone

*For special requests, please contact AMS

Specifications

Model	Rejection %			Flux LMH	Membrane Area	Feed Spacer
Wiodei	Glucose	NaCl	MgSO ₄	(GFD)	m^2 (ft ²)	mil
A-3012-2540-31N					1.9 (20)	31
A-3012-2540-31P]				1.5 (20)	
A-3012-2540-46N					1.6 (17)	46
A-3012-2540-46P	96	40	96	90 (53)	1.0 (17)	10
A-3012-4040-31N	, ,,	10		70 (33)	6.5 (70)	31
A-3012-4040-31P					0.5 (70)	31
A-3012-4040-46N					5.2 (56)	46
A-3012-4040-46P					3.2 (30)	.0

Test Conditions: 40 bar (580 psi), 30° C (86°F), Flux measured with RO water, Feed solutions for rejection tests are 3% glucose /3.2% NaCl/ 0.2% MgSO₄ in RO water. Permeate flux may vary for individual element but it will no more than 25% below the above value.



Operating Information(*)

Maximum Operating Pressure: 70 bar (1015 psi)

Maximum Operating Temperature: 80°C (176°F)

Maximum Cleaning Temperature: 80°C (176°F)

Allowable pH – Continuous Operation: 0-12 Allowable pH – Clean in Place (CIP): 0-13

Maximum Pressure Drop per Element: 0.5 bar (7.2 psi)

2540: Minimum 7.5 L/min (2 gpm), Maximum 19 L/min (5 gpm) Recirculation Flow Rate

4040: Minimum 22 L/min (6 gpm), Maximum 65 L/min (17 gpm)


(*) Consult AMS Technologies for specific information

Recommended cleaning materials

- Depending on the nature of the feed material, a choice can be made from the following cleaning agents:
 - Sodium hydroxide at pH 10-12, 40°C (104°F)
 - Nitric or hydrochloric acid at pH 1-2, 40°C (104°F)
 - 0.2-1% w/w Na-EDTA, pH 10.5-11, 35°C (91°F)
 - 0.5% anionic surfactant (such as SDS), pH 10.5-11, 35°C (91°F)
- Water quality for cleaning:
 - Maximum turbidity is 1 NTU

Nominal Product Dimensions

For 2540/4040:



Size	A	В	С	D
	mm (inches)	mm (inches)	mm (inches)	mm (inches)
2540	1016 (40)	61 (2.4)	19 (0.75)	954 (37.5)
4040	1016 (40)	99 (3.9)	19 (0.75)	965 (38)



Lubricants:

For element installation, use only water or glycerin to lubricate seals. The use of petroleum or vegetable-based oils or solvents may damage the element and void any warranty.

Preservation

• Short Term (up to two weeks): 0.25% w/w sodium metabisulfite.

Storage

• The membrane should not be allowed to dry. It should be stored in a sealed bag, at 4°-30°C (39-86°F).

Acid Stability:

Typical solutions include:

20% H₂SO₄ 20% HCl 4%HNO₃

30% H₃PO₄ 15% Acetic acid

Our membranes run at high and stable fluxes in very acidic environment for 12 months and more.

Other

• Do not expose the membrane to chlorine or other oxidants.